

Mattosil Facade Paint 960



Silicone reinforced, with a mineral character, matt, weather resistant, for exterior use



Color System

Field of application

For weather-resistant, water-repellent facade coatings on load-bearing mineral substrates, e.g. exterior plaster, concrete, brick masonry as well as intact dispersion paint coats and organically bonded renders. On surfaces exposed to moisture (depending on location and construction) there is a risk of algal and fungal infestation. For such surfaces we recommend using Mattosil Facade Paint 960 in "Protect quality" (for further information, refer to Notes).

Properties

- Silicone-reinforced
- Highly weather-resistant
- Mineral character
- Very good filling power
- Water-repellent
- Low tension
- Low odor
- Non-saponifiable
- Water-vapor-permeable
- Resistant to industrial emissions
- Easy to apply
- Optionally available in Protect quality (film protection against an algal and fungal infestation of the coating)

Material description

Color shades	0095 white Light and medium color shades can be mixed with the Brillux Color System.
Color stability	Fb code B1–3, depending on color shade, according to BFS Leaflet no. 26.
Base material	Acrylate copolymer
Density	Approx. 1.50 g/cm ³

Material description

Classified in accordance with DIN EN 1062	S1	Grain size: fine
	E3	Dry film thickness > 100 to ≤ 200 µm, depending on system build-up.
	G3	Degree of gloss: matt
	V1	Medium water-vapor permeable, s_d (H ₂ O) approx. 0.14 m according to DIN EN ISO 7783.
	W3	Low water permeability, w-rate < 0.1 kg/(m ² ·h ^{0.5})
Packaging	0095 white: 15 l Color System: 2.5 l, 10 l, 15 l	

Use

Dilution	If necessary, thin slightly with water.
Tinting	With Full Color and Tinting Paint 951.
Compatibility	Can only be mixed with materials of the same type and those specified in this data sheet.
Application	Mattosil Facade Paint 960 can be applied by using a brush, roller or airless spray application. Optimal results are achieved with high efficiency through the use of low-overspray airless spraying. For more information, refer to information leaflet 2ns2. (Note the information about "Protect quality").
Consumption	Approx. 150 to 200 ml/m ² per coat on smooth substrates. Consumption increases on rough surfaces accordingly. Determine the exact consumption by means of a test application on the object to be coated.
Application temperature	Do not apply if air or object temperature is below +5°C
Tool cleaning	Clean tools with water immediately after use.

Spray data

Spray system	Nozzle	Spray angle	Pressure	Thinning
Airless	0.021–0.027 inch	40°–80°	150 bar	Approx. 5–10%

Spray data for low-overspray facade coatings

Spray system	Nozzle	Spray angle	Pressure		Thinning	
			Banking-up pressure	Spray pressure	with heating hose	without heating hose
Low-Overspray Airless Spraying	0.027 inches	40°	150–200 bar	100–130 bar	Unthinned, possibly up to 5%	up to 5%

Further information and order details for accessories are summarized in the "Low-overspray airless spraying 2ns2" information leaflet.

Drying (+20°C, 65% relative humidity)

Coatable after approx. 12 hours.
Allow longer drying times at lower temperatures and/or higher air humidity.

Storage

Store in a cool and frost-free place. Reseal opened containers tightly.

Declaration

Notes Contains preservatives.
Do not inhale spray mist.

Product code BSW20.
Comply with the specifications in the current safety data sheet.

Coating build-up

- Substrate preparation**
- The substrate must be solid, dry, clean, load-bearing and free from efflorescence, sinter layers, separating agents, corrosion-promoting components or other intermediate layers affecting the adhesion.
 - Remove fine-grained layers on concrete surfaces mechanically or by means of pressure washing.
 - If the substrate is exposed to moisture, fast water run-off is to be ensured.
 - Protect horizontal surfaces by taking appropriate design measures
 - Check the suitability, load-bearing capacity and adhesive properties of existing coatings.
 - Thoroughly remove defective and unsuitable coatings and dispose of them in accordance with the applicable regulations.
 - Sand down and clean smooth and dense substrates.
 - Clean surfaces infested with fungi and algae thoroughly, then treat them with Universal Disinfectant 542* (* Use biocides carefully. Always read the label and product information before use.).
 - Treat replastered areas with a fluorine primer; if the subsequent paint coat is to be tinted, prime the entire surface.
 - See also VOB Part C, DIN 18363, Section 3

Substrates ¹⁾	Prime coat	Intermediate coat	Top coat
Exterior substrates with normal absorption capacity, e.g. exterior plaster (depending on the compressive strength ²⁾)	Depending on the individual requirements, Priming Concentrate 938 which has been diluted 1 : 4 parts, or Lacryl Deep Penetrating Primer 595	Mattosil Facade Paint 960 or – if filling and smoothing properties are required – Silicone Brush Filler 910	Mattosil Facade Paint 960
Highly absorbent exterior substrates, e.g. exterior plaster (depending on the compressive strength ²⁾ , concrete ³⁾)	Depending on the individual requirements, Lacryl Deep Penetrating Primer 595 or Deep Penetrating Primer 545		
Non-absorbent substrates	Depending on the requirements, Adhesion Primer 3720 ⁴⁾ , 2K-EP Varioprimer 865 or 2K-EP Varioprimer S 864		

¹⁾ We recommend using Evocryl 200 or Silicone Facade Paint 918 for coating untreated, asbestos-free fiber cement boards. For coating asbestos cement claddings, follow the instructions provided in the “Coating Systems for Asbestos Facade Cladding 2asb” data sheet.

²⁾ Minimum compressive strength > 2.0 N/mm² (compressive strength category CS II and CS III)

³⁾ In the case of dense, non- or slightly absorptive concrete, e.g. pre-fabricated concrete parts, apply a test sample using Adhesion Primer 3720, if necessary.

⁴⁾ Pretreat defects prior to the prime coat with Deep Penetrating Primer 545 or Lacryl Deep Penetrating Primer 595.

Contiguous surfaces	Only use material from the same batch on a contiguous surface or mix the required material quantity.
Touch-ups	Touch-ups to part of a surface are always visible. The degree to which they stand out depends on the situation on site. According to BFS Leaflet no. 25, Section 4.2.2.1, Paragraph e, this is unavoidable.
Lime efflorescence on concrete	There is a risk of lime efflorescence on concrete facade surfaces. A pore-free coating film prevents penetration of external water and minimizes this risk. To achieve an intact coating, existing pores, holes and honeycombing must be filled in advance by means of Concrete Pore Filler 782 for example. In event of cracks, use crack-bridging coating systems with a product such as Concrete Finish 839 or Concrete Elast OS 862.
New mineral substrates	Allow new mineral substrates, in particular plaster surfaces (limestone cement mortar and cement mortar), at least 14 days or ideally 4 weeks to cure and dry properly before further coating. Depending on the weather and time of year, the drying process may take even longer.
Protect quality	Containers marked with "Protect" contain material that is optimized in the factory with film preservation against algal and fungal infestation. The material may only be used outdoors. The contained preservatives minimize and/or delay the risk of algal and fungal infestation. The material enhanced by adding film preservation must be applied with sufficient layer thickness. We recommend application of at least two layers. With the current state-of-the-art technical development, a permanent protection against algal and fungal infestation cannot be guaranteed. Spray application to vertical surfaces is possible when using low-overspray airless spraying. Do not inhale spray mist and always wear protective clothing.
Glossy streaks in the case of early exposure to moisture	If exposed to moisture too soon after application (condensation or rain), water-soluble wetting agents can be released in high concentrates from the coating film and appear as glossy streak marks on the coating surface. If such stains occur, do not immediately re-coat the surfaces. The water-soluble materials will be washed off by moisture (rain) again in the course of time. However, if immediate recoating is to be performed, thoroughly wash off the streaks with water beforehand. To avoid this, only carry out the coating work when weather conditions are favorable.
Structural protection	Window sills and adequately dimensioned covers prolong the service life of facade coatings. Missing drip edges or drip edges that are too close to the building/facade (according to BFS Leaflet no. 9, Notes I) can lead to visible stains and soiling on facades, balustrades, etc. within a relatively short time.
Further information	Follow the instructions in the data sheets of the products used.

Remark

This data sheet is based on extensive development work and years of practical experience. The translation corresponds to the current German version, in compliance with the German laws, regulations, standards and guidelines. Its content does not constitute a contractual legal relationship. The user/buyer is not released from the responsibility of checking our products to ensure they are suitable for the intended application. In addition, our general terms of business apply.

When a new version of this data sheet with updated information is published, the previous version no longer applies. The current version is available on our website.

Brillux
Weseler Straße 401
48163 Münster
GERMANY
Phone +49 251 7188-0
Fax +49 251 7188-105
info@brillux.de
www.brillux.com